IBS MARINE SUPPLIES

Everything for Inflatables

# INFLATABLES ANTIFOULING - DATA SHEET

An antifouling characterised by its elasticity and recommended for rubber dinghies.
This antifouling is highly effective and ideal for painting neoprene surfaces, rubber fabric, PVC and Hypalon. It has excellent flexibility and adhesion.

**PHYSICAL CHARACTERISTICS**

Curing mechanism : ..... Thinner evaporation
Specific weight : ..... 1.20 kg/l
Dry volume : ..... 22 %
Flash point : ..... 23°C <= PE <= 55°C
Texture : ..... Mat
Colour : .....Black, Grey

**PREPARATION OF SURFACE**

To ensure a perfect paint adhesion, clean the surface thoroughly. Remove all traces of rubber dust with a cloth impregnated with a solvent. It is imperative to dilute the antifouling from 10 to 15 % with the thinner. Only paint onto a dry surface.

**APPLICATION**

Mix the antifouling for several minutes in order to ensure it is completely uniform. Apply 2 coats with interval of 8 hours, the craft should be inflated to 80% Wait 24 to 48 hours after the second coat before re-inflating the craft. The boat should not be launched until at least 24 hours after the application of the last coat (maximum 2 months). Only apply with a brush surface.

**CHARACTERISTICS FOR USE**

Drying time before use (20°C) : ..... Minimum 24 hours
Pot life : ..... /
Application temperature : ..... Between + 5 and + 35°C Hardener :
..... /
Wet film thickness per coat : ..... 70 µ
Dry film thickness per coat : ..... 15 µ
Practical coverage per coat : ..... 12 m2/l
Overcoating time : ..... 8 hours
Number of coats : ..... 2
Dilution: ..... 10 to 15 % with the thinner

**PACKING AND STORAGE**

Packaging : ..... 750 cc
Storage : ..... In closed container away from heat, cold and damp

**PRECAUTIONS FOR USE**

Wear gloves, goggles and protective clothes. Do not smoke when using.

**HEALTH AND SAFETY**

See data sheet

This information corresponds to the actual state of our knowledge and has the sole object of informing you about our products and possible applications. It is objectively given but does not imply any guarantee by us. Our company may modify all these details at any time.